



Polyart IML 130

- HDPE voided film
- Simultaneous biaxial orientation
- Heat reactive adhesive layer
- Grid pattern to avoid blisters

Property	Method	Units	Typical values
Weight	ISO 536:1995	lbs	54 (500 sheets 25" x 38")
Thickness	ISO 534:2005	mils	5.1
Density		g/cm ³	0.62
Whiteness	TAPPI 1216 SP-07	%	90
Opacity	ISO 2471:2008	%	92
Tensile strength	ISO 527-3:1995	lbs/in ²	
MD			4890
TD			3935
Elongation at break	ISO 527-3:1995	%	
MD			85
TD			50
Tear strength	ASTM D1004-66	lbs/in	
MD			270
TD			390
Surface Resistivity	ASTM D-257	Ω/□	<10 ¹⁴
Stiffness (Gurley)	TAPPI T543	mg	53

Features and Benefits

- Compatible with HDPE blow molded bottles
- Designed for wheel type machines
- Suitable for use with many printing techniques including UV offset and gravure printing
- No grain direction due to simultaneous biaxial stretching technology

Advice in this document is based on practical field experience and is given in good faith but Arjobex, the manufacturer of Polyart synthetic papers, may not be held liable for loss or damage arising from action based on this information. Arjobex recommends all qualifications be conducted with our technical team.

