


# ARJOBEX



## Polyart 140 GSM C2S

- HDPE voided film
- Simultaneous biaxial orientation
- Coated two sides

PROPERTY	TEST METHOD	UNITS	VALUE
Thickness	ASTM: D645-92	Mils	7.0
		Microns	175
Weight	ASTM: D646-92 (95)	g/m <sup>2</sup>	140
		lbs: 500 sheets-25"x38"	95
Density		g/m <sup>2</sup>	0.82
Whiteness	ISO 2470	%	90
Opacity	ASTM: D589-94	%	97
Gloss	ASTM: D523-89	%	12
Tensile Strength	ASTM: D638-95	lbs/in <sup>2</sup>	MD: 5790 TD: 4630
Elongation	ASTM: D638-95	%	MD: 130 TD: 130
Tear Strength	ASTM: 1004-66	lbs/in	MD: 457 TD: 612
Stiffness (Gurley)	TAPPI T543	mg	200
Fold 180		Times	>5X10 <sup>4</sup>
Surface Resistivity	ASTM: D-257	Ω/□	<10 <sup>14</sup>

## Features and Benefits

- Excellent stiffness for conversion & automatic label dispensing
- Resists wide temperature variations: -60°C to +60°C
- Good opacity and water resistance
- Excellent thermal transfer printing with a wide range of ribbons
- Excellent printing and ink drying by conventional printing methods
- Die-cuts extremely well
- No static issues
- High dimensional stability
- Resistant to a wide range of chemicals
- Recyclable with other polyolefins

The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary information.