


# ARJOBEX



## Polyart® 75 GSM C2S

- Clay coated two sides
- Highly cavitated & filled HDPE film
- Simultaneous biaxial orientation

PROPERTY	TEST METHOD	UNITS	VALUE
<b>Thickness</b>	ASTM: D645-92	Mils	3.8
		Microns	97
<b>Weight</b>	ASTM: D646-92(95)	g/m <sup>2</sup>	75
		500 shts-25"x38"	51
<b>Density</b>		g/cm <sup>3</sup>	0.79
<b>Whiteness</b>	ISO 2470	%	90
<b>Opacity</b>	ASTM: D589-94	%	92
<b>Gloss</b>	ASTM: D523-89	%	12
<b>Tensile Strength</b>	ASTM D638-95	lbs/in <sup>2</sup>	MD: 6525 TD: 5075
<b>Elongation</b>	ASTM: D638-95	%	MD: 110 TD: 100
<b>Tear Strength</b>	ASTM: D1004-66	lbs/in	MD: 540 TD: 570
<b>Stiffness (Gurley)</b>	TAPPI T543	mg	70
<b>Fold 180</b>		Times	>5x10 <sup>4</sup>
<b>Surface Resistivity</b>	ASTM: D-257	Ω/□	<10 <sup>14</sup>

## Features and Benefits

- Recommended for coating with hot melt adhesives
- Best thermal transfer printability for permanent self-adhesive labels
- Great dimensional stability
- Film withstands frozen/cryogenic temps when combined with appropriate adhesive
- Matte clay coating 2 sides
- Highly conformable, no grain direction
- Good stiffness allows excellent label dispensing

The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary information.