

- FSC® Certified paper
- Outdoor & moisture resistant coating
- Short term outdoor exposure

Property	Method	Units	Typical Values		
Weight	DIN 53104	g/m <sup>2</sup>	215	365	
Thickness	DIN 53105	mil	9	15	
Cobb (30 mn)	DIN 53132	g/cm <sup>2</sup>	<30	<50	
Smoothness Beck	DIN 53107	s	FS	190	100
			RS	120	100
Whiteness	ISO 2470	%	110	110	
Opacity	ISO 2471	%	99.3	99.9	

FS: front side - RS: reverse side

*Advice in this document is based on practical field experience and given in good faith but the manufacturer of Fiberskin may not be held liable for loss or damage arising from action based on this information.*

## Features and Benefits

- Fiberskin® is biodegradable
- Recyclable paper
- FSC® certified\*
- PVC free
- Laser printable
- Good water resistance (against splash water, rain) \*\*
- Convert like paper and board

\* Fiberskin® is a product of MDV part of the Polyart Group FSC®-C084527

\*\* 6 to 8 weeks for direct exposure to bad weather, 6 months under shelter

**Storage:** keep in unopened and undamaged original packaging at temperatures of 20-25°C in relative humidity conditions of 50%. Avoid the influence of damaging factors such as humidity, heat or direct sunlight on the product, and thereby protect it.

We are not aware of any other circumstances which may affect the quality when stored correctly. Nonetheless, we recommend that the material be used latest within one year of the manufacturing date.

**Usage:** after transport and storage in cold rooms the material should be adjusted to the printing room's climate (1h / cm of roll diameter or stack high).