




**MAIN ATTRIBUTES:**

- Filled HDPE film-highly cavitated core
- Simultaneous biaxial orientation
- Heat reactive adhesion layer
- Grid pattern to avoid blisters



Property	Method	Units	Typical values
<b>Thickness</b>	<b>ISO 534:2011</b>	<b>Mils</b>	<b>4.5</b>
		<b>Microns</b>	<b>114</b>
<b>Weight</b>	<b>ISO 536:2012</b>	<b>g/m<sup>2</sup></b>	<b>80</b>
<b>Density</b>	<b>ISO 534:2011</b>	<b>g/cm<sup>3</sup></b>	<b>0.7</b>
<b>Whiteness</b>	<b>TAPPI 1216 SP-12</b>	<b>%</b>	<b>90</b>
<b>Opacity</b>	<b>ISO 2471:2008</b>	<b>%</b>	<b>92</b>
<b>Surface resistivity</b>	<b>ASTM D-257-14</b>	<b>Ω/□</b>	<b>&lt;10<sup>14</sup></b>
<b>Dyne level</b>	<b>ASTM D2578-09</b>	<b>Dynes/cm</b>	<b>&gt;42</b>



**FEATURES AND BENEFITS:**

**PRINTING:**

- Sheet-fed offset & web (offset, flexo, gravure)
- No Machine Direction

**RECYCLING:**

- Compatible for mono-component HDPE bottles
- HDPE substrate for PP & PE blow-molding compatibility
- 100% compatible with regrind PE/PP bottles

**BLOW-MOULDING:**

- Blister free engineered grid pattern
- Full adhesion at low temperatures
- Anti-blocking for high-speed pick & place robotics
- Compatible with shuttle & wheel blow moulding

**BOTTLE TYPE:**

- Small labels
- Smooth light orange peel

The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary information.